

# NEW FROM UCAN

FASTENING PRODUCTS

# FLO-ROK FRG

## ANCHORING CEMENT

### DESCRIPTION

FLO-ROK FRG is a fast setting, high strength, hydraulic type anchoring cement. As it hardens, it expands to fill voids and develops 2000 psi compressive strength in 2 hours at room temperature. Controlled water additions allow the product to be used in packable (vertical) or pourable (horizontal) applications. To ensure optimal performance of FRG, the hole diameter should be at least 1" (25 mm) larger than the post being fastened. The minimum recommended embedment is 2" (50 mm).

### TYPICAL APPLICATIONS

- Anchoring of wood or metal sign posts, fence post parking meters
- Dowel and rod installation horizontal applications
- Handrail installation
- Setting appliances, machinery and processing equipment
- Door stops
- Ornamental ironwork installation surface staining.

### LIMITATIONS

- Hot temperature will speed up setting
- At colder temperatures, below 10 °C (50 °F) use warm water
- Do not apply over surfaces that are frozen or contain frost.



### MATERIAL SPECIFICATION

Composition and Materials: FRG Anchoring Cement is a combination of special cements and silica sand

Yield: 50 lbs pail (22.7 kg) will yield 0.42 cu.ft (0.012m<sup>3</sup>) mixed anchoring material

Color: Grey

Sizes: 11.9 lbs (FRG-12) and 50 lbs (FRG-50)

Physical Properties: Setting time: (ASTM C 191) Final set – 10 to 30 min.

Compressive Strength (ASTM C109)

2 hrs.	2,000 psi (13.8 MPa)
24 hrs.	4,000 psi (27.6 MPa)
7 days	6,000 psi (41.4 MPa)
28 days	7,000 psi (48.3 MPa)

## NOW AVAILABLE FROM STOCK

### UCAN FASTENING PRODUCTS

155 Champagne Drive, Unit 10  
Toronto, Ont., M3J 2C6 Canada

TEL.: 416-631-9400  
FAX: 416-631-9426

E-MAIL: sales@ucanfast.com  
www.ucanfast.com

U.S.A.  
TEL.: (800) 461-8226